

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

- 1-10. (Cancelled).
11. (Previously Presented) A method for making polymer-coated single-wall carbon nanotubes comprising dispersing single-wall carbon nanotubes and a polymer in a solvent by a method selected from the group consisting of mixing, sonication, heating and combinations thereof, wherein the solvent comprises water and wherein the polymer is water-soluble.
12. (Previously Presented) A method in accordance with claim 11, wherein the single-wall carbon nanotubes are substantially free of amorphous carbon.
13. (Previously Presented) A method in accordance with claim 11, wherein the single-wall carbon nanotubes are coated with at least two polymers.
14. (Previously Presented) A method in accordance with claim 11, wherein the polymer and the plurality of individual single wall carbon nanotubes are added to the solvent sequentially.
15. (Previously Presented) A method in accordance with claim 11, wherein the polymer and the plurality of individual single-wall carbon nanotubes are added to the solvent simultaneously.
16. (Cancelled)
17. (Previously Presented) A method in accordance with claim 11, wherein the solvent further comprises a surfactant.
18. (Previously Presented) A method in accordance with claim 11, wherein the concentration of single-wall carbon nanotubes in the solvent is between about 0.1 grams/liter and about 5 grams/liter.

19. (Previously Presented) A method in accordance with claim 11, wherein the concentration of polymer in the solvent is between about 1.0 percent and about 5.0 percent by weight.

20. (Previously Presented) A method for making polymer-coated single-wall carbon nanotubes comprising dispersing single-wall carbon nanotubes and a polymer in a solvent by a method selected from the group consisting of mixing, sonication, heating and combinations thereof, wherein the solvent is heated to a temperature at least about 40 °C.

21. (Previously Presented) A method in accordance with claim 20, wherein the solvent is heated to a temperature of between about 50 °C and about 60 °C.

22. (Previously Presented) A method for making polymer-coated single-wall carbon nanotubes comprising dispersing single-wall carbon nanotubes and a polymer in a solvent by a method selected from the group consisting of mixing, sonication, heating and combinations thereof, wherein the solvent is heated between about 0.1 hours and about 100 hours.

23. (Previously Presented) A method in accordance with claim 22, wherein the solvent is heated between about 1 hour and about 50 hours.

24. (Currently Amended) A method in accordance with claim 11, further comprising the step of extruding the polymer-~~wrapped~~coated nanotubes with a second polymer to form an encapsulated nanotube-polymer composite.

25. (Previously Presented) A method comprising:

(a) dispersing single-wall carbon nanotubes and a polymer in a first solvent by a method selected from the group consisting of mixing, sonication, heating and combinations thereof to make polymer-coated single-wall carbon nanotubes; and

(b) removing the polymer coat from the nanotubes by contacting the coated nanotubes with a second solvent having a low surface tension.

26. (Previously Presented) A method in accordance with claim 25, wherein the second solvent comprises a chlorinated hydrocarbon.

27. (Previously Presented) A method in accordance with claim 11, further comprising the step of aligning the nanotubes by application of an external field selected from the group consisting of an electrical field, a magnetic field and a shear flow field.

28-46. (Cancelled)

47. (Previously Presented) A method in accordance with claim 11, wherein the polymer is selected from the group consisting of polyvinyl pyrrolidone (PVP), polystyrene sulfonate (PSS), poly(1-vinyl pyrrolidone-co-vinyl acetate) (PVP/VA), poly(1-vinyl pyrrolidone-co-acrylic acid), poly(1-vinyl pyrrolidone-co-dimethylaminoethyl methacrylate), polyvinyl sulfate, poly(sodium styrene sulfonic acid-co-maleic acid), dextran, dextran sulfate, bovine serum albumin (BSA), poly(methyl methacrylate-co-ethyl acrylate), polyvinyl alcohol, polyethylene glycol, and polyallyl amine.

48. (Previously Presented) The method in accordance with claim 11, wherein the single-wall carbon nanotubes are dispersed with at least two different polymers.

49. (Previously Presented) A method in accordance with claim 11, wherein the solvent is heated to a temperature at least about 40 °C.

50. (Previously Presented) A method in accordance with claim 49, wherein the solvent is heated between about 0.1 hours and about 100 hours.

51. (Previously Presented) A method in accordance with claim 11, wherein the solvent is heated to a temperature of between about 50 °C and about 60 °C.

52. (Previously Presented) A method in accordance with claim 51, wherein the solvent is heated between about 1 hour and about 50 hours.

53. (Previously Presented) A method in accordance with claim 11, wherein the solvent is heated between about 0.1 hours and about 100 hours.

54. (Previously Presented) A method in accordance with claim 11, wherein the solvent is heated between about 1 hour and about 50 hours.

55. (Previously Presented) The method in accordance with claim 17, wherein the surfactant is sodium dodecyl sulfate (SDS).

56. (Previously Presented) A method in accordance with claim 20, wherein the single-wall carbon nanotubes are coated with at least two polymers.

57. (Previously Presented) The method in accordance with claim 20, wherein the single-wall carbon nanotubes are dispersed with at least two different polymers.

58. (Previously Presented) A method in accordance with claim 20, wherein the solvent further comprises a surfactant.

59. (Previously Presented) The method in accordance with claim 58, wherein the surfactant is sodium dodecyl sulfate (SDS).

60. (Previously Presented) A method in accordance with claim 20, wherein the concentration of single-wall carbon nanotubes in the solvent is between about 0.1 grams/liter and about 5 grams/liter.

61. (Previously Presented) A method in accordance with claim 20, wherein the concentration of polymer in the solvent is between about 1.0 percent and about 5.0 percent by weight.

62. (Previously Presented) A method in accordance with claim 20, wherein the solvent is heated between about 0.1 hours and about 100 hours.

63. (Previously Presented) A method in accordance with claim 20, wherein the solvent is heated between about 1 hour and about 50 hours.

64. (Currently Amended) A method in accordance with claim 20, further comprising the step of extruding the polymer-~~wrapped~~coated nanotubes with a second polymer to form an encapsulated nanotube-polymer composite.

65. (Previously Presented) A method in accordance with claim 20, further comprising the step of aligning the nanotubes by application of an external field selected from the group consisting of an electrical field, a magnetic field and a shear flow field.

66. (Previously Presented) A method in accordance with claim 20, wherein the polymer is selected from the group consisting of polyvinyl pyrrolidone (PVP), polystyrene sulfonate (PSS), poly(1-vinyl pyrrolidone-co-vinyl acetate) (PVP/VA), poly(1-vinyl pyrrolidone-co-acrylic acid), poly(1-vinyl pyrrolidone-co-dimethylaminoethyl methacrylate), polyvinyl sulfate, poly(sodium styrene sulfonic acid-co-maleic acid), dextran, dextran sulfate, bovine serum albumin (BSA), poly(methyl methacrylate-co-ethyl acrylate), polyvinyl alcohol, polyethylene glycol, and polyallyl amine.

67. (Previously Presented) A method in accordance with claim 22, wherein the single-wall carbon nanotubes are coated with at least two polymers.

68. (Previously Presented) The method in accordance with claim 22, wherein the single-wall carbon nanotubes are dispersed with at least two different polymers.

69. (Previously Presented) A method in accordance with claim 22, wherein the solvent further comprises a surfactant.

70. (Previously Presented) The method in accordance with claim 69, wherein the surfactant is sodium dodecyl sulfate (SDS).

71. (Previously Presented) A method in accordance with claim 22, wherein the concentration of single-wall carbon nanotubes in the solvent is between about 0.1 grams/liter and about 5 grams/liter.

72. (Previously Presented) A method in accordance with claim 22, wherein the concentration of polymer in the solvent is between about 1.0 percent and about 5.0 percent by weight.

73. (Currently Amended) A method in accordance with claim 22, further comprising the step of extruding the polymer-~~wrapped~~coated nanotubes with a second polymer to form an encapsulated nanotube-polymer composite.

74. (Previously Presented) A method in accordance with claim 22, further comprising the step of aligning the nanotubes by application of an external field selected from the group consisting of an electrical field, a magnetic field and a shear flow field.

75. (Previously Presented) A method in accordance with claim 22, wherein the polymer is selected from the group consisting of polyvinyl pyrrolidone (PVP), polystyrene sulfonate (PSS), poly(1-vinyl pyrrolidone-co-vinyl acetate) (PVP/VA), poly(1-vinyl pyrrolidone-co-acrylic acid), poly(1-vinyl pyrrolidone-co-dimethylaminoethyl methacrylate), polyvinyl sulfate, poly(sodium styrene sulfonic acid-co-maleic acid), dextran, dextran sulfate, bovine serum albumin (BSA), poly(methyl methacrylate-co-ethyl acrylate), polyvinyl alcohol, polyethylene glycol, and polyallyl amine.

76. (Previously Presented) A method in accordance with claim 25, wherein the second solvent comprises tetrahydrofuran.

77. (New) A method in accordance with claim 11, further comprising the step of adding salt in a quantity effective to promote coating of the polymer on the single-wall carbon nanotubes to form polymer-coated single-wall carbon nanotubes.

78. (New) A method in accordance with claim 77, wherein the salt is selected from the group consisting of an alkali metal salt and an alkaline earth metal salt.

79. (New) A method in accordance with claim 77, wherein the salt comprises sodium chloride

80. (New) A method in accordance with claim 20, further comprising the step of adding salt in a quantity effective to promote coating of the polymer on the single-wall carbon nanotubes to form polymer-coated single-wall carbon nanotubes.

81. (New) A method in accordance with claim 80, wherein the salt is selected from the group consisting of an alkali metal salt and an alkaline earth metal salt.

82. (New) A method in accordance with claim 80, wherein the salt comprises sodium chloride.

83. (New) A method in accordance with claim 22, further comprising the step of adding salt in a quantity effective to promote coating of the polymer on the single-wall carbon nanotubes to form polymer-coated single-wall carbon nanotubes.

84. (New) A method in accordance with claim 83, wherein the salt is selected from the group consisting of an alkali metal salt and an alkaline earth metal salt.

85. (New) A method in accordance with claim 83, wherein the salt comprises sodium chloride.

86. (New) A method for making polymer-wrapped single-wall carbon nanotubes comprising dispersing single-wall carbon nanotubes and a polymer in a solvent by a method selected from the group consisting of mixing, sonication, heating and combinations thereof.